



sv to

No soaking





Pastethe-wall technique



Minimal paint usa



Covers cracks



Easy to remove

## How to use



**1**. Remove old wallpaper and paint. Smooth out rough base surfaces with plaster-based filler. Prime very absorbent base surfaces with solvent-free primer.




2a. Use a pasting machine without soaking or



**2b.** Use with the paste-the-wall technique without soaking







**6**. Do not overlap in corners and at edges, but separate precisely along the edge and butt joint the next length.

4. Use a wallpapering brush or rubber roller to press out bubbles and folds.



**7.** When dry, paint with high-quality emulsion paint in line with EN 13300 or possibly plaster, wallpaper or similar.



**5.** Use a Stanley knife and palette knife to trim off excess material at ceilings, skirting boards or windows etc.



**8**. When you come to redecorate, the wallpaper can be removed with ease.





# Technical Data Sheet 06/2022

# **Product Description**

### **ERFURT-Variovlies M 140**

#### Manufacturer

ERFURT & SOHN KG • Hugo-Erfurt-Straße 1 42399 Wuppertal • GERMANY • www.erfurt.com

#### Raw materials/Manufacture

ERFURT-Variovlies M 140 is a flat wallcovering, manufactured from special cellulose and textile fibres, combined with polymer binding agents.

### Product data

- Order no. 1000549
- Roll dimensions: 25.00 m long x 1.00 m wide
- Carton content: 4 rolls
- Weight: approx. 140 g/m<sup>2</sup>

### Product features

- Covers contrasting colours on base surfaces very well
- In the majority of cases one coat of paint is sufficient
- Its water vapour permeability as per DIN 52615 corresponds to a diffusion-equivalent air layer thickness of approx. 0.01 m.
- Fire rating "B-s1,d0" according to EN 13501-1 (fire-retardant)
- Free of PVC, plasticisers and solvents harmful to health
- Fibreglass-free
- No addition of heavy metal compounds or formaldehyde
- Dimensionally stable and covers cracks
- Very durable when used with appropriate paints
- · Easy to remove after moistening with water
- Can be re-painted several times with commercially available paints

# **Application/Handling**

#### **Base surface**

Ensure that the base surface is dry, firm, even, absorbent, clean, smooth and sufficiently even for the intended wallcovering. Remove old wallpaper and loose paint. Smooth out rough base surfaces with plaster-based filler. Prime smooth plaster with diluted paste. Prime highly absorbent base surfaces with solvent-free primer or paste. Please read BFS data sheets nos. 7 and 16.

#### **Base surface for painting**

Old, cracked plaster or similar, that should only be painted after appropriate preparation. Creates an evenly-textured surface for paint, for instance mixed base surfaces (plaster, visible concrete or plasterboard).

#### For covering cracks and for wall design:

Henkel: Solvite Ready to Roll, Delicate Wallcoverings Adhesive Pufas: Glutolin S15, Glutolin K10, Decotric GK

On non-absorbent base surfaces, such as plastic walls: Pufas: Glutolin BW, Decotric WB

ERFURT-Variovlies M 140 can be hung without the need for soaking. Hang ERFURT-Variovlies M 140 perpendicular, with the lengths butt jointed to each other. Depending on the level of wear and tear the wall will be subjected to, apply emulsion paint with minimum wet abrasion class 3 (as per EN 13300).

Alternatively the wallpapered surface can be painted in an airless process. If doing so, it is necessary to subsequently roll the surface with a short pile paint roller to obtain a clean and even appearance.

### Base surface for wallpaper

Can be wallpapered over using any type of wallcovering if applied to a smooth surface. Use the paste specified for use with this type of wallcovering, but at the very least special adhesive at a ratio of 1:20 (200 g in 4 litres of water), to hang wallpaper onto ERFURT Variovlies M 140. Owing to the strength of ERFURT-Variovlies M 140, all wallcoverings that have been hung using paste, can be subsequently removed with ease. Any damage can be made good with conventional plaster filler. ERFURT-Variovlies M 140 can therefore be papered over many times.

# Ingredients/Test results

Its water vapour permeability as per DIN 52615 was certified by the ISEGA-Forschungs- und Untersuchungs-Gesellschaft mbH in Aschaffenburg, Germany.

Phone.: +49 202 6110 0 Fax: +49 202 6110 89 451 E-mail: info@erfurt.com Website: www.erfurt.com

